



Semi-enclosed  
dinonylnaphthalene  
disulfonic acid

## **Product introduction**

Semi-enclosed dinonylnaphthalene  
disulfonic acid catalyst

## **Chemical composition**

Dinonylnaphthalene disulfonic acid

## **Characteristic advantage**

1. The best comprehensive performance;
2. Excellent adhesion;
3. Good salt spray resistance;
4. Good moisture resistance.

## **Recommended use**

1. General industrial paint system;
2. Coil, water-based cans, home appliance coatings;
3. Electrostatic spraying coating;
4. Car primer.

## **Recommended dosage**

0.5-2.0% of resin solids.

## **Technical data**

Active Ingredients:	60±2%
Solvent:	Isobutanol
PH value:	4-6
Specific Gravity:	0.94
Color ratio:	≤10
Appearance:	Dark brown liquid

## **Processing guidance**

1. Minimum curing temperature 90°C;
2. Add the following paragraph.

## **Storage and transportation**

1. Cool, dry and ventilated, below 60°C, do not approach the fire;
2. Shelf life is two year in sealed container.

## **Package**

25kg or 200KG package.

We provide these data and technical advice with our existing knowledge. However, because of the different application environment, please users according to the test application, we can not guarantee all the circumstances.

JIANGSU BRILN EPT CO.,LTD.  
Xinbei District Changzhou Jiangsu  
Tel:0519-81884271 Fax:0519-85788271